



Test Report

No: TX91525 /2007 /PL

Date: OCT. 01, 2007

Page: 1 OF 2

TUNG FONG TEXTILE CO., LTD.
NO. 6, SI-AN RD, HOMEI CHANGHUA
508 TAIWAN R.O.C

The following sample was submitted and identified by the client as:

SAMPLE DESCRIPTION: ONE SAMPLE OF SUNSCREEN FABRIC 87% PVC 13% POLYESTER
40X32/250DX250D IN WHITE/BEIGE

STYLE NO.: F70-036

COUNTRY OF ORIGIN: TAIWAN


SAMPLE RECEIVING DATE: SEP. 20, 2007

TEST STARTING DATE: SEP. 20, 2007

Test Performed: Selected test(s) as requested by applicant.

Test Results: For further details, please refer to the following page(s).

Signed for and on behalf of
SGS Taiwan Ltd.


Chen Chun Ni, Ginny
Testing Specialist

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or available on request and accessible at www.sgs.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this report is unlawful and offenders may be prosecuted to the fullest extent of the law. 此報告是遵循本公司訂定之通用服務條款所製作發放，請注意此條款列印於背面，亦可在www.sgs.com中查閱。將本公司之義務，免責，管轄權皆明確規範之。除非另有說明，此報告結果僅對檢驗之樣品負責。本報告未經本公司書面許可，不可部份複製。對本報告內容或外觀之任何未經授權之變更、偽造、竄改皆屬非法，違犯者將會被依法追訴。

TW 5355415



Test Report

No: TX91525 /2007 /PL

Date: OCT. 01, 2007

Page: 2 OF 2

Test Results:

1. Stiffness Of Fabrics (AATM D1388-1996 (2002) Option A, Cantilever Test)

Bending length (cm)

Warp 6.8

Weft 5.9

Flexural rigidity (mg.cm)

Warp 15,819.3

Weft 10,767.9

Note: The test was subcontracted to other SGS Laboratory.

2. Tensile Strength (ASTM D5035-06 - 2C-E Cut Strip method)

Warp direction 367.3 lbf

Filling direction 288.2 lbf

Note: The test was subcontracted to other SGS Laboratory.

*** End of Report ***

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or available on request and accessible at www.sgs.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this report is unlawful and offenders may be prosecuted to the fullest extent of the law. 此報告是遵照本公司訂定之通用服務條款所製作發放，請注意此條款列印於背面，亦可在www.sgs.com中查閱。將本公司之義務，免責，管轄權皆明確規範之。除非另有說明，此報告結果僅對檢驗之樣品負責。本報告未經本公司書面許可，不可部份複製。對本報告內容或外觀之任何未經授權之變更、偽造、竄改皆屬非法，違犯者將會被依法追訴。

TW 5355416